

# Netiquette 1241

Schema 1295

## Specifications

---

### Contents

68% polyester  
32% post-consumer recycled polyester

### Weight

9.6 ± 1.0 oz./lin. yd.

### Width

66" min. useable

### Repeat

7.25" vertical | 14" horizontal  
Random match

### Treatment

polyester binder

### Backing

none

### Treatment

polyester binder

## Cleaning Code

---

<p>Standard Care Label W-S. Clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup. May also be disinfected with hydrogen peroxide, alcohol, and quaternary ammonium (quat) based cleaners.</p>

## Performance

---



### Breaking Strength (ASTM D5034)

250 lbf min. warp and 130 lbf min. fill

### Tear (ASTM D2261)

15 lbf min. warp and fill

### Colorfastness to light (AATCC 16.3 Option 3)

Grade 4 min. at 40 hours

### Colorfastness to crocking (AATCC 8)

Grade 4 min. dry & Grade 3 min. wet

### NRC of anechoic termination


1.00

### NRC of fabric in front of anechoic termination

.95

## Miscellaneous

---



The plot below summarizes impedance tube measurements of absorption of an anechoic termination and various fabrics in front of the anechoic termination.

Acoustical Performance for Panel Applications  
(ISO 10534-2)

