

# Napa 2954

Calistoga 9012

## Specifications

---

### Contents

100% FR polyester

### Weight

13.0 ± 1.0 oz./lin. yd.

### Width

72" min. useable

### Repeat

26.3" vertical, 18.9" horizontal

### Treatment

Antimicrobial

### Backing

none

### Treatment

Antimicrobial

## Cleaning Code

---

<p>Standard Care Label W-S. Commercial wash at 160&deg;F maximum wash temperature using detergents recommended for the type of washing machines being used, no chlorine bleach. Rinse warm. Do not overload the washer as this may result in inadequate cleansing of the fabric and excessive wrinkling. Dry on synthetic (cool) setting until slightly damp or just dry. Do not overload the dryer. Over-drying or drying at hot temperatures may cause unacceptable shrinkage to occur. If necessary, press with a cool iron (&ldquo;polyester&rdquo; or &ldquo;synthetics&rdquo; setting, max temp 275&deg; F). May also be disinfected with hydrogen peroxide, alcohol, and quaternary ammonium (quat) based cleaners.</p>

## Performance

---



### Breaking Strength (ASTM D5034)

175 lbf min. warp and 90 lbf min. fill

### Tear (ASTM D2261)

10 lbf min. warp and fill

### Seam Slippage (ASTM D4034)

60 lbf min. warp and fill

### Colorfastness to light (AATCC 16.3 Option 3)

Grade 4 min. at 60 hours

### Colorfastness to crocking (AATCC 8)

Grade 4 min. dry & Grade 3 min. wet

### Flammability

NFPA 701 TM#1 Pass

## Miscellaneous

---

Every effort has been made to ensure color accuracy of the digital images, however, please order a sample before specification. Application testing of this product is recommended. Colors may vary between dye lots. This is a directional fabric. Binder card not available.

Proudly woven in North America supporting our local communities.

