

# Pebble 4769

Schoolhouse 1505

## Specifications

### Contents

70% polyester  
20% antimony-free polyester  
7% pre-consumer recycled polyester  
3% post-consumer recycled polyester

### Weight

10.8 ± 1.0 oz./lin. yd.

### Width

54" min. useable

### Repeat

31.6" vertical | 12.75" horizontal

### Treatment

stain repellent

### Backing

acrylic backcoating

### Treatment

stain repellent

### Backing

acrylic backcoating

## Cleaning Code

<p>Standard Care Label W-S. Clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup. May also be disinfected with hydrogen peroxide, alcohol, and quaternary ammonium (quat) based cleaners.</p>

## Performance



### Breaking Strength (ASTM D5034)

255 lbf min. warp and 130 lbf min. fill

### Tear (ASTM D2261)

25 lbf min. warp and 35 lbf min. fill

### Seam Slippage (ASTM D4034)

100 lbf warp and 55 lbf fill

### Pilling resistance (ASTM D3511)

Class 4

### Colorfastness to light (AATCC 16.3 Option 3)

Grade 4 min. at 40 hours

### Colorfastness to crocking (AATCC 8)

Grade 4 min. dry & Grade 3 min. wet

### Wyzenbeek Abrasion resistance (ASTM D4157)

100,000 double rubs cotton duck

### Flammability

CA Technical Bulletin 117-2013 Section 1

## Miscellaneous

Proudly woven in North America supporting our local communities. Application testing of this product is recommended. Colors may vary between dye lots. This is a directional fabric.



