# Metallation 5118

**Polished Pewter** 1678

# **Specifications**

#### **Contents**

56% post-consumer recycled polyester 44% polyester

#### Weight

 $15.2 \pm 0.5$  oz./lin. yd.

#### Width

66" min. useable

# Repeat

none

#### **Treatment**

none

### **Backing**

none

# **Cleaning Code**

Standard Care Label W-S. Clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup. May also be disinfected with hydrogen peroxide, alcohol, and quaternary ammonium (quat) based cleaners.

## **Performance**









## **Breaking Strength (ASTM D5034)**

150 lbf min. warp and fill

#### Tear (ASTM D2261)

30 lbf min. warp and fill

# Colorfastness to light (AATCC 16.3 Option 3)

Grade 4 min. at 40 hours

### Colorfastness to crocking (AATCC 8)

Grade 4 min. dry & Grade 3 min. wet

#### **Flammability**

ASTM E84 Class I or A

## NRC of anechoic termination

1.00

#### NRC of fabric in front of anechoic termination


.95


# **Miscellaneous**

Every effort has been made to ensure color accuracy of the digital images, however, please order a sample before specification. Application testing of this product is recommended. Colors may vary between dye lots. This is a directional fabric.

Proudly woven in North America supporting our local communities.

Pre-Approved: Haworth, Herman Miller, HNI and Trendway.







The plot below summarizes impedance tube measurements of absorption of an anechoic termination and various fabrics in front of the anechoic termination.

# Acoustical Performance for Panel Applications (ISO 10534-2)

